

## PAROC CGL 20cyc

### Ceiling lamella



Certification Number	0809-CPR-1015 / Eurofins Expert Services Ltd, P.O. Box 1001, FI-02044 VTT, Finland
Designation Code	MW-EN13162-T5-DS(70,90)-CS(Y)20-TR20-WS-WL(P)-MU1-AFr10
Short Description	Rigid, fire safe stone wool lamella with high thermal insulation performance. The edges are cutted on one side of the lamella and coating is done on both sides.
Application	Thermal, fire and sound insulation of ceilings. Connected to the base by adhesive. The surface of this product can be painted.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

### Dimensions

Dimensions	
Width x Length	Thickness
200 x 1200 mm	50 - 200 mm
In accordance with EN 822	In accordance with EN 823

Dimensional Stability		
Property	Value	According to
Dimensional Stability under Specified Temperature and Humidity Conditions, DS(70,90)	≤ 1 %	EN 13162:2012 + A1:2015 (EN 1604)

### Packaging

Package Type	Plastic package, Plastic Packages on a Pallet or Loose Product on a Pallet
--------------	--

## Fire Properties

Reaction to Fire		
Property	Value	According to
Reaction to Fire, Euroclass	A1	EN 13162:2012 + A1:2015 (EN 13501-1)

Continuous Glowing Combustion		
Property	Value	According to
Continuous Glowing Combustion	NPD	EN 13162:2012 + A1:2015

Other Fire Properties		
Property	Value	According to
Combustibility	Non-combustible	EN ISO 1182

## Thermal Properties

Thermal Resistance		
Property	Value	According to
Thermal Resistance	<a href="#">See attachment</a>	EN 13162:2012 + A1:2015
Thermal Conductivity $\lambda_D$	0,037 W/mK	EN 13162:2012 + A1:2015
Thickness Tolerance, T	T5	EN 13162:2012 + A1:2015 (EN 823)

Direct Airborne Sound Insulation Index		
Property	Value	According to
Air Flow Resistivity $AF_R$	NPD	EN 13162:2012 + A1:2015 (EN 29053)

## Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term $W_S$ , $W_p$	$\leq 1 \text{ kg/m}^2$	EN 13162:2012 + A1:2015 (EN 1609)
Water Absorption, Long Term $W_L(P)$ , $W_{lp}$	$\leq 3 \text{ kg/m}^2$	EN 13162:2012 + A1:2015 (EN 12087)

Water Vapour Permeability		
Property	Value	According to
Water Vapour Resistance Z	NPD	EN 13162:2012+A1:2015
Water Vapour Transmission $MU$ , $\mu$	1	EN 13162:2012 + A1:2015 (EN 12086)

## Sound Properties

Acoustic Absorption Index		
Property	Value	According to
Sound Absorption	NPD	EN 13162:2012 + A1:2015 (EN ISO 354)

Impact Noise Transmission Index (for Floors)		
Property	Value	According to
Dynamic Stiffness $SD$	NPD	EN 13162:2012 + A1:2015 (EN 29052-1)

## Mechanical Properties

Compressive Strength		
Property	Value	According to
Compressive Stress at 10 % deformation CS(10), $\sigma_{10}$	NPD	EN 13162:2012 + A1:2015 (EN 826)
Compressive Strength CS(Y), $\sigma_m$	20 kPa	EN 13162:2012 + A1:2015 (EN 826)
Point Load PL(5)	NPD	EN 13162:2012 + A1:2015 (EN 12340)

Property	Value	According to
Compressibility CP	NPD	EN 13162:2012 + A1:2015

Tensile/Flexural Strength		
Property	Value	According to
Tensile Strength Perpendicular to Faces TR, $\sigma_{mt}$	20 kPa	EN 13162:2012 + A1:2015 (EN 1607)

## Emissions

Release of Dangerous Substances to the Indoor Environment		
Property	Value	According to
Release of Dangerous Substances	NPD	EN 13162:2012 + A1:2015

## Durability

Durability of Compressive Strength against Ageing/Degradation		
Property	Value	According to
Compressive Creep CC(i1/i2/y) $\sigma_c$ , $X_{ct}$	NPD	EN 13162:2012 + A1:2015 (EN 1606)

**Durability of Reaction to Fire Against Heat, Weathering, Ageing/Degradation**  
 The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of product is related to the organic content, which cannot increase with time.

**Durability of Thermal Resistance Against Heat, Weathering, Ageing/Degradation**  
 Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

## Facings

**Facing Material** Silicate based, sprayed coating

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, [www.paroc.com](http://www.paroc.com)

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).