

PAROC Marine Navis Mat 60



Short Description

Stone wool mat. Also possible to use with facing AluCoat and G4. See "Facings".

Application

Fire and thermal insulation on ships.

The notified body Eurofins Expert Services Ltd. (0809) performed and issued the certificates: Type-Examination (Module B) certificate No. VTT-C-12315-15-18

Nominal Density

60 kg/m³

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Dimensions	
Width x Length	Thickness
Width 600 or 1000 mm, length 2000 - 8000 mm, depending on thickness	30-100 mm
In accordance with EN 822	In accordance with EN 823

Packaging

Package Type

Plastic packs on pallet.

Fire Properties

Other Fire Properties		
Property	Value	According to
Fire Classification (IMO)	Non-Combustible	IMO FTP 2010 Code Part 1


Thermal Properties

Thermal Conductivity (values announced by manufacturer)		
Property	Value	According to
Thermal Conductivity in 10 °C, λ ₁₀	0,032 W/mK	EN 12667
Thermal Conductivity in 50 °C, λ ₅₀	0,038 W/mK	EN 12667

Thermal Conductivity in 100 °C, λ_{100}	0,045 W/mK	EN 12667
Thermal Conductivity in 150 °C, λ_{150}	0,054 W/mK	EN 12667
Thermal Conductivity in 200 °C, λ_{200}	0,063 W/mK	EN 12667
Thermal Conductivity in 300 °C, λ_{300}	0,086 W/mK	EN 12667
Thermal Conductivity in 400 °C, λ_{400}	0,116 W/mK	EN 12667
Thermal Conductivity in 500 °C, λ_{500}	0,153 W/mK	EN 12667

Values announced by the manufacturer.


Facings



AluCoat



G4



G7

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).