

PAROC ROB 80t

Roof board



Certification Number

0809-CPR-1015 / Eurofins Expert
Services Ltd, P.O. Box 1001, FI-
02044 VTT, Finland

Designation Code

MW-EN13162-T5-DS(70,-)-
CS(10)80-PL(5)700-WS-WL(P)-MU1

Short Description

Very rigid, fire safe stone wool board
with high thermal insulation
performance and load bearing
capacity. It is faced with natural
coloured glass tissue.

Application

Roofing board developed to provide
sustainable fire safe bedding for most
types of flat roofs, and as thermal
insulation and bearing layer in
renovation sites.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Dimensions	
Width x Length	Thickness
1200 x 1800 mm	20 - 30 mm
In accordance with EN 822	In accordance with EN 823

Dimensional Stability		
Property	Value	According to
Dimensional Stability at Specified Temperature, DS(70,-)	≤ 1 %	EN 13162:2012 + A1:2015 (EN 1604)

Other Dimensions

Other sizes available on request.

Packaging

Package Type On a wooden pallet bearers are of stone wool

Fire Properties

Reaction to Fire		
Property	Value	According to
Reaction to Fire, Euroclass	A1	EN 13162:2012 + A1:2015 (EN 13501-1)

Continuous Glowing Combustion		
Property	Value	According to
Continuous Glowing Combustion	NPD	EN 13162:2012 + A1:2015

Other Fire Properties		
Property	Value	According to
Combustibility	Non-combustible	EN ISO 1182

Flat roofs insulated with stone wool means a better insurance against big catastrophes at fire.

Thermal Properties

Thermal Resistance		
Property	Value	According to
Thermal Resistance	See attachment	EN 13162:2012 + A1:2015
Thermal Conductivity λ_D	0,038 W/mK	EN 13162:2012 + A1:2015
Thickness Tolerance, T	T5	EN 13162:2012 + A1:2015 (EN 823)

Direct Airborne Sound Insulation Index		
Property	Value	According to
Air Flow Resistivity AF_R	NPD	EN 13162:2012 + A1:2015 (EN 29053)

Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term W_S, W_p	$\leq 1 \text{ kg/m}^2$	EN 13162:2012 + A1:2015 (EN 1609)
Water Absorption, Long Term $W_L(P), W_{lp}$	$\leq 3 \text{ kg/m}^2$	EN 13162:2012 + A1:2015 (EN 12087)

Water Vapour Permeability		
Property	Value	According to
Water Vapour Resistance Z	NPD	EN 13162:2012+A1:2015
Water Vapour Transmission MU, μ	1	EN 13162:2012 + A1:2015 (EN 12086)

Flat roofs insulated by stone wool can keep moisture and dry out when the circumstances in climate is available.

Sound Properties

Acoustic Absorption Index		
Property	Value	According to

Sound Absorption	NPD	EN 13162:2012 + A1:2015 (EN ISO 354)
------------------	-----	--------------------------------------

Impact Noise Transmission Index (for Floors)

Property	Value	According to
Dynamic Stiffness SD	NPD	EN 13162:2012 + A1:2015 (EN 29052-1)

Mechanical Properties

Compressive Strength

Property	Value	According to
Compressive Stress at 10 % deformation CS(10), σ_{10}	80 kPa	EN 13162:2012 + A1:2015 (EN 826)
Compressive Strength CS(Y), σ_m	NPD	EN 13162:2012 + A1:2015 (EN 826)
Point Load PL(5)	700 N	EN 13162:2012 + A1:2015 (EN 12340)

Compressibility CP

Property	Value	According to
Compressibility CP	NPD	EN 13162:2012 + A1:2015

Tensile/Flexural Strength

Property	Value	According to
Tensile Strength Perpendicular to Faces TR, σ_{mt}	NPD	EN 13162:2012 + A1:2015 (EN 1607)

Emissions

Release of Dangerous Substances to the Indoor Environment

Property	Value	According to
Release of Dangerous Substances	NPD	EN 13162:2012 + A1:2015

Durability

Durability of Compressive Strength against Ageing/Degradation

Property	Value	According to
Compressive Creep CC(i1/i2/y) σ_c , X _{ct}	NPD	EN 13162:2012 + A1:2015 (EN 1606)

Durability of Reaction to Fire Against Heat, Weathering, Ageing/Degradation

The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of product is related to the organic content, which cannot increase with time.

Durability of Thermal Resistance Against Heat, Weathering, Ageing/Degradation

Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

Facings

Facing Material Glass fibre tissue

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).